

JP69029554

## ANSWER 1 OF 1 WPIX:

ACCESSION NUMBER: 1968-42985Q [00] WPIX  
TITLE: Polypropylene fabric finishing to improve properties.  
DERWENT CLASS: A00  
PATENT ASSIGNEE(S): (MITR) MITR; (MITR) MITSUBISHI RAYON CO LTD  
COUNTRY COUNT: 1  
PATENT INFORMATION:

PATENT NO	KIND	DATE	WEEK	LA	PG
-----					
JP 44029554	B		(196800)*		

PRIORITY APPLN. INFO: JP 1966-81914 19661214

AN 1968-42985Q [00] WPIX

AB JP 69029554 B UPAB: 19930831

Polypropylene is mixed with 1-30% of mixture of 25-5% polyethylene and 75-95% low mol. wt. n-paraffin, spun and fabric produced, and treated with treating agent after drying at > 130 deg.C but < melting pt. of polypropylene.

Can be used to improve colouring, flame-resistance, anti-static properties, crease-resistance, abrasion-resistance, anti-oxidn., softening, etc. and wash-resistant finish is obtd.

Suitable polyethylene has mol. wt. 12,000-120,000 and sp. gr. > 0.92 (obtd. by low, intermediate or high pressure process)

Suitable n-paraffin is paraffin, crystalline wax or polyethylene of average mol. wt. 500-3000.

Treating agent may be dye, pigment, size, water-proofing agent, flame-proofing agent, U. V. absorber, anti-oxidant, antistat, softener, etc.